

ABSTRACT OF THE DISCLOSURE

The SMNR of a granular perpendicular recording medium is significantly enhanced by incorporating TiO_2 at the grain boundaries of the magnetic alloy layer. Embodiments include granular perpendicular recording media comprising CoPt alloys containing 0.1 to 15 at.% TiO_2 and a molar ratio of Pt:Co of up to 0.5.

WDC99 842474-1.050103.0546